

## Data Sheet

# KIMYA PA6-CO 3D FILAMENT

## Nylon 6 copolymer additive manufacturing filament

### DESCRIPTION

Kimya PA6-CO is a 3D printing filament made from a Nylon 6-based copolymer. This unfilled polyamide stands out for its excellent tensile strength, low warping, and ease of use—even on open-chamber printers. Unlike many other nylon filaments, PA6-CO combines strong mechanical, chemical, and heat resistance with user-friendly printability, making it an ideal standard polyamide for functional parts and industrial applications. As with all polyamides, the filament should be dried before printing to ensure optimal results.

### BENEFITS

- Strong and Reliable.
- Low Warping Behavior.
- Chemical and Heat Resistant.

### TECHNICAL DATA

Properties	Values	Test Methods
Diameter	1.75 ± 0.1 mm 2.85 ± 0.1 mm	INS-6712
Density	1.157 g/cm <sup>3</sup> (0.042 lb/in <sup>3</sup> )	ISO 1183-1
Glass transition temperature (T <sub>g</sub> )	65°C (149°F)	ISO 11357-1 DSC (10°C/min-20-300°C)
Melting Temperature (T <sub>m</sub> )	227°C (440°F)	ISO 11357-1 DSC (10°C/min-0-300°C)
Properties	Values	Test Methods
Tensile Modulus	2,166 MPa (314.2 ksi)	ISO 527-2/1A/50
Tensile Strength	56.1 MPa (8.14 ksi)	ISO 527-2/1A/50
Tensile Strain at Strength	4.3 %	ISO 527-2/1A/50
Tensile Stress at Break	13.4 MPa (1.94 ksi)	ISO 527-2/1A/50
Tensile Strain at Break (type A)	< 14 %	ISO 527-2/1A/50
Flexural Modulus	2,017 MPa (292.5 ksi)	ISO 178
Deformation at Flexural Strain	< 5 %	ISO 178
Flexural Stress at Conventional Deflection (3.5% Strain)*	65.9 MPa (9.56 ksi)	ISO 178
Charpy Impact Resistance	3.9 kJ/m <sup>2</sup> (1.85 ft-lbs/in <sup>2</sup> )	ISO 179-1/1eA
Shore Hardness	77.3 D	ISO 868

### PROCESSING

Printing Direction	<b>XY</b>
Printing Speed	50-60 mm/s
Nozzle Temperature	265°C - 275°C (509°F - 527°F)
Bed Temperature	70°C - 80°C (158°F - 176°F)

### SUSTAINABILITY



Can be recycled



Recyclable packaging

### NOTES

- \*According to ISO 178, end of the test at 5% deformation even if there is no specimen break.
- The data should be considered as indicative values - Properties can be influenced by production conditions.

Last updated : 2025-12-22

Catalogue position : **KIMYA Filaments for Additive Manufacture**